


# AIR FORCE STATION, DELHI : Effectiveness of Thermacool Coatings



**Location:**  
Empty Storage Ware House, Air Force Station, Race Course Road,  
Delhi.



# AIR FORCE STATION : Effectiveness of Thermacool Coatings



18-20 °C

TANGIBLE  
REDUCTION





### SUMMARY OF DATA COLLECTED ( All in Centigrade)

	BEFORE APPLICATION	AFTER APPLICATION	DIFFERENCE
OUTDOOR ROOF TEMPERATURE	52.7	33.6	19 °C
INSIDE DECK TEMPERATURE	46.2 - 46.9	32.3-32.7	14 °C
INSIDE AMBIENT TEMPERATURE	35.7 - 35.9	26.8	9 °C
INSIDE FLOOR TEMPERATURE	34.2	25.1	9 °C

